RG104 E-1 Box 121

1880

Weekly Report of Gold Deposits Melted at United States Mint.

Date.	Assay No.	Name of Depositor.	Weight before Melting. oz.	dec.	Weight after Melting. oz.	dec.	Loss. oz.	dec.	Loss per ct.		Gain. oz.	dec.	Description of Bullion.	Notes of Melter & Refiner. 4/29/80
April 19th	669	G. C. Thompson	8	97	8	16		81	9	00			Mch Cases & Jewelry	The deposits are from the following sources:
	70	do	11	49	11	49							Bars	
	1	Johnson & Lund	8	88	8	74		14	1	86			Dpt & Fillings	Virginia (1) 1
	2	Abraham Harris	64	38	61	48	2	90	4	53			Mch Cases & Jewelry	N. Carolina (1) 2
	3	R. Poat	10	20	10	20							Bullions	Georgia 1
	4	Wm. H. Lee	63	40	63	40							Bar	Colorado (1) 1
	5	G. C. Thompson	44	47	43	18	1	29	2	93			Jewelry Mch Cases	Wyoming 1
	6	L. R. Bord	17	97	16	90	1	07	5	94			Mch Cases & Jewelry	Fine bullion (3) 8
	7	Jas. MacKintosh	11	74	11	74							Bullion	Less fine " 3
20th	8	G. C. Thompson	16	88	11	15	5	68	33	41			Bars, Base	Jewelry, &c. " 7
	9	do	29	89	28	85	1	04	3	47			Jewelry, Mch Cases &c. Silver	very base " 3
	80	Zeigler Bros.	7	45	7	33		12	1	71			Amt, N. Co.	Dent. Plate 1
	1	John Castner, Cash[r]	2	28	2	33					05		Bars & Pieces, Va.	Total 28
21st	2	G. C. Thompson	16	42	16	35		07		44			Bars	
	3	do	12	82	11	20	1	62	12	46			Jewelry, Bar, Dpt, &c.	The loss on the N. Carolina amalg. 1.71%
	4	S. H. Gerecke	24	24	21	93	3	31	13	79			Ring, Base	is less than usual; —
	5	G. C. Thompson	4	42	4	24		18	4	50			Mch Case, Jewelry, &c.	as is that of the Georgia
	6	A. Loudon Snowden, Supt.	125	35	125	31		04		03			Bars, N. C. Mint	amalgam, 1.63%;
22nd	7	Drexel & Co.	21	96	21	64	1	32	6	00			Amt, Wyoming	on the Wyoming Amalg.
	8	H. Muhr's Sons	23	67	23	60		07		29			Bars	6.00%, is usual; —
23d	9	G. C. Thompson	19	39	19	08		31	1	63			Amt, Geo.	on the finer bullion,
	90	do	12	37	11	08	1	29	10	75			Mch Cases & Jewelry	on Silver 0.07%, is much
	1	do	31	70	29	95	1	98	6	09			Bullion, Bar & Silver	less than is usually the
	2	do	19	80	19	70		10		50			Bars & Pieces	case; — on the less
	3	A. Loudon Snowden, Supt.	480	35	480	13		22		05			Bars, Denver Mint	fine bullion, 7.63%,
	4	Hagstoz & Thorpe	55	78	55	78							Bar	is more full than is
24th	5	G. C. Thompson	7	92	6	13	1	79	22	37			Leaf	usually the case; —
	6	do	10	73	9	81		92	8	36			Bars	on Jewelry &c. 7.01%
	7	H. Muhr's Sons	17	84	17	84							Bars	is unusually low;
	8	Reitel & Kinsler	7	44	6	85		59	8	43			Bars	on the very base
			1190	15	1163	37	26	83	2	39	05			23.19% is reasonably near the general average of such bullion.

Received from U. S. R. C. N. Y., during the week and transferred immediately to the Melter & Refiner 293,497.86 Oz. in Bars.

Jas C Booth
Melter & Refiner

For week ending April 24th 1880
Approximate value, $ 18.032.23

To the Director of the Mint.

J. Robley Dunglison
Register.

RG104 E-1 Box 121

Report of Gold Deposits
Melted for Week ending
April 24th 1850

NARA RG104, Entry 1, Box 121

[Abstract:] Report of Gold Deposits melted for week ending April 24, 1880

Weekly Report of Gold Deposits Melted at United States Mint.

[Please see original images for data table.]